
t 1002

## BEST AVAILABLE COPY

Second Edition

HANDBOOK OF PULP & PAPER TERMINOLOGY

A Guide to Industrial and Technological Usage
by Gary A. Smook



## BEST AVAILABLE COPY

Copyright @2001 by Gary A. Smook

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, electronic or mechanical. including photocopying, recording, or otherwise without prior written permission from the author, except for inclusion of brief quotations in a review.

While no effort has been spared to make this handbook as complete and accurate as possible, it may contain typographical errors or mistakes in content. This handbook should be used only as a general guideline, and not as the ultimate or authoritative source of technical information. The author and Angus Wilde Publications Inc. shall have neither liability nor responsibility to any person or entity with respect to any loss or damage caused, or alleged to be caused, directly or indirectly, by information contained in this book.

Published by: Angus Wilde Publications Inc.

4543 West 11th Avenue

Vancouver, B.C. V6R 2M5 Canada

Available in

Angus Wilde Publications Inc. the USA from:

P.O. Box 1036

Bellingham, WA 98227-1036 USA

## Canadian Cataloguing in Publication Data

Smook, G. A. (Gary A.), 1934-

Handbook of pulp & paper terminology: a guide to industrial and technological usage

2nd ed. Includes index. ISBN 0-9694628-4-0

1.Wood-pulp industry--Terminology, 2, Paper industry-Terminology. I. Title.

TS1085.S66 2001

676'.03

C00-901646-5

Printed and bound in Canada Design and layout by Hilda Wiebe

## BEST AVAILABLE COPY

Cellulose Chemistry CHAPTER 4

quid used nufacture cture with /clic com-

ther celluther celluthere is some acidifithere of shortd 90. See JAMMA-

nisms. Iny are cerar the bio-

ganic comtimals. For tin synthe-

blank proof a given value obdeulate the

ms, groups inations of ganic com-

ange in pH

te acids and eaction and

with a calins on either by the time i to flow by ifflux time). i to measure

nounds syndrogen and e usually in lose, sugars hemistry of af two funcbonyl group. CARBON DISULFIDE: (CS<sub>2</sub>) Colorless, volatile liquid with a characteristic odor, used as a solvent in the viscose process. Syn. Carbon Bisulfide.

CARBONYL GROUP: Divalent organic radical C=O, characteristic of aldehydes, ketones and carboxylic acids. Carbonyl groups are formed on the cellulose molecule during bleaching.

CARBOXYL GROUP: Radical -COOH of an organic acid. Carboxyl groups are formed on cellulose fibers by oxidation during pulping and bleaching processes. In paper pulps, the carboxyl groups contribute to the bonding of fibers and to the retention of rosin size; but these groups also provide ion exchange capacity, and absorbed cations contribute to discoloration during drying.

CARBOXYMETHYLCELLULOSE (CMC): Cellulose in which CH<sub>3</sub>COOH groups are substituted on the glucose units of the cellulose chain through an ether linkage. Since the reaction takes place in alkaline media, the usual product is the sodium salt. It is a hydrophilic colloid with physical properties that depend on the extent of etherification, CMC has found application as a pigment coating binder.

CATALYST: Substance that promotes or accelerates a chemical reaction without being consumed by it. A catalyst may either be unaffected by the reaction or enter into the reaction and then be reformed.

CELLOBIOSE: Alternating arrangement of two glucose residues. Cellobiose units are joined together to form molecular chains of cellulose. See also MAUTOSE.

CELLOPHANE: Generic name for transparent film of regenerated cellulose used for wrapping.

CELLULASE: Extracellular enzyme produced during the growth of fungi, bacteria, insects and other lower animals that hydrolyzes cellulose.

CELLULOLYTIC: [adj] Term used to describe organisms that have the ability to hydrolyze cellulose.

**CELLULOSE**: (C<sub>6</sub>H<sub>10</sub>O<sub>5</sub>)<sub>6</sub> Material that forms the solid framework or cell walls of all plants; the most abundant organic compound in nature. It is a straight-chain (linear) polysaccharide composed of repeating glucose residues (or more precisely, cellobiose units), the number of which can vary over a wide range.

CELLULOSE ACETATE: White, flaky material produced by acetylation of cellulose, of which two forms are commercially important. A modified, partially hydrolyzed form (DS of 2.2 to 2.5) is used in the production of fibers, films and plastics. The "triacetate" (DS of at least 2.8) is used in the production of fibers. Most cellulose acetate products are made by solvent evaporation methods. See also DEGREE OF SUBSTITUTION.

CELLULOSE ACETATE BUTYRATE: White flaky material produced according to butyrol content by reacting cellulose with various mixtures of acetic and butyric anhydrides, used for molding compositions.

CELLULOSE ESTER: Cellulose in which the free hydroxyl groups have been replaced wholly or in part by acidic groups, e.g., cellulose acetate, cellulose propionate.

CELLULOSE ETHER: Cellulose in which the free hydroxyl groups have been wholly or partially converted to others by reaction with alcohols, e.g., methyl cellulose, ethyl cellulose.

CELLULOSE FIBER: Natural cellulosic material derived from wood or other plant materials by pulping and bleaching operations.

CELLULOSE FILM: See CELLOPHANE.

CELLULOSE MODIFICATION: Chemical reaction by which some or all of the substituent radicals of cellulosc are replaced by other chemical entities (for example, hydroxyls replaced by carboxyl or alkyl radicals). Modified cellulose retains its general structure, but has altered properties.

CELLULOSE NITRATE: Product obtained by treating cellulose with a mixture of concentrated nitric and sulfuric acids, used as explosive and propellant. Syn. Nitrocollulose.

CELLULOSE PROPIONATE: White flaky material produced by reacting cellulose with propionic anhydride, used for molding compositions.

CELLULOSE TRIACETATE: See CELLULOSE ACETATE.

CELLULOSE VISCOSITY: Property of a pulp or other cellulosic material which is expressed by the viscosity of a dilute solution of the material in a suitable solvent under specified conditions. The viscosity is related to the molecular DP, and thus to the strength and other properties of the fibers. See also CUENE.

CELLULOSIC: Collective term referring to any of the numerous compounds and products made by reacting cellulose with various chemicals, usually involving substitution of the hydroxyl groups of the cellulose. The products include regenerated cellulose (e.g., rayon or cellophane), cellulose acetate, nitrocellulose, and methylcellulose.

CHEMICAL ACCESSIBILITY: Extent to which cellulose and other carbohydrates are available for chemical reactions, a function of the index of order.

CHEMICAL ANALYSIS: Analytical method using chemical techniques.

CHEMICAL CELLULOSE: Highly processed pulp with high alpha cellulose content, used for chemical conversion into such products as viscose rayon and cellulose acetate. Syn. Dissolving Pulp.

CHEMICAL COTTON: Chemical cellulose prepared from cotton, usually from cotton linters.